



DYNAMIC EXIM CORPORATION

241-242, Indraprasth, Near Nobat Press, Pancheshwar Tower Road, Jamnagar - 361001. Gujarat, INDIA.

Tel.: +91 288 2675560

Cell: +91 98250 83001

Mail: info@calcinedkaolinindia.com

Fax: +91 288 2556844

Cell: +91 94262 07061

Web: www.calcinedkaolinindia.com

Meta Kaolin

PRODUCT SPECIFICATION

GRADE NAME	MK 75
Application	Ultramarine Blue / Pigment
Pow. BR (%) ISO	75±2
Color Shade (on water panel)	Creamish Pink
Bulk Density (gms/lit)	350-400
PH	5-7
Residue	1.0% Max
Oil Absorption (gm/100gm)	55-56
Hegman Grind	4.5
Specific Gravity	2.5 - 2.7
Loss on Drying (at 105°C/hrs)	0.5% max

CHEMICAL COMPOSITION

% SiO ₂	51-53
% Al ₂ O ₃	41-43
% Fe ₂ O ₃	1.0
% TiO ₂	1.5
% CaO	0.5
% MgO	0.2
% Na ₂ O	0.25
% K ₂ O	0.25
% L.O.I.	0.8